

**EXHIBIT “A”**  
**Request for Bid (RFB)**  
**Procurement Packet**

## HOT MIX ASPHALTIC CONCRETE PAVEMENT (LIMESTONE)

### MATERIAL

Hot Mix Asphaltic Concrete, Type "D" (fine graded surface course) (Limestone). The hot mix asphaltic concrete shall conform to the requirements of the Texas State Department of Highways & Special Provisions 340-115, dated 10-88, with antistripping agent in accordance with Special Specifications Item 3373. The successful bidder shall submit an asphalt mix design within ten (10) days upon award of contract from a geotechnical laboratory demonstrating that the hot mix asphaltic concrete to be used meets these specifications. The asphalt to be used shall be A. C. 20. Special Modifications to Standard Specification Item 340, for the project are as follows:

1. Asphalt Content

Asphaltic Material (AC-20) shall form, from 4 to 8.0 percent of the mixture by weight.

2. Retained Stability

The paving mixture shall have a retained stability of not less than 70 percent when tested in accordance with ASTM standard procedure D1075.

3. Hveem Stability

Hveem Stability shall not be less than 30 percent.

4. All aggregate shall be 100% crushed limestone.

5. Mix shall contain a minimum of 85 percent limestone.

END OF SECTION