




P.O. Box 2724
McAllen, Tx. 78502
(956) 585-3773

SIGNATURE 
R# 501038
PO# 885818

Invoice

Date	Invoice #
2/6/2025	30079

Please send remittance with copy of invoice to:

Attn: Mrs. Aisha Gonzalez
P.O. Box 2724
McAllen, Tx. 78502

Bill To:

Hidalgo County Precinct #3
724 Breyfogle Rd.
Mission, TX 78574

Project Info:

C-24-0247-08-06
WA#1 - Veterans Memorial Pavilion
(ARPA-21-123-023)
PO# 885818
B2Z JOB #: 3104

Billing Period January 2025



Description	Contract	Previous Applications	Current Completed	Total Completed	% Complete
Construction Material Testing Services (CMT)	\$ 35,050.20	\$ 10,515.06	\$ 3,505.02	\$ 14,020.08	40.0%
Total For This Billing Period					\$3,505.02

Work Authorization ~ Summary

WA No.	WA Amount	Previously Inv.	Percent Complete	Remaining Balance
1	\$35,050.20	\$10,515.06	40%	\$21,030.12


Aisha Gonzalez - President

Acct# 5-1290-441-67-115-218-3-740

INVOICE RECEIVED BY  ON 2-10-25
GOODS/SERVICES RECEIVED BY  ON 2-10-25

Mission Office

900 S Stewart Rd, Ste. 2
Mission, TX 78572
Phone: 956-585-3773

Client:

Hidalgo County Precinct No. 3
724 Breyfogle Rd
Mission, TX 78574

Project:

3104
Veterans Memorial Pavilion
300 S. Inspiration Rd.
Mission, TX 78572

Sample Details			
Set #:	2	Technician:	Jacob Chavez
Specimen Size:	4 x 8 Cast Cylinder	Cast By:	Jacob Chavez
Specimens In Set:	5	Date Cast:	12/06/24
Truck / Ticket #:	107 / 99585	Sampled From:	Chute
Contractor:	8A Builders	Placement Method:	Chute
		Batched:	12:12 CST
		Sampled:	12:45 CST
		Cast:	12:55 CST
		Truck Empty:	13:10 CST
		Placement Time:	58 (min)

Location	
Placement Location:	Concrete Paving - Sidewalk
Location Details:	300 S Inspiration Rd
Sample Location / Notes:	West side of sidewalk

Batch Log		Specifications	
Supplier:	Transit Ready Mix	Mix Design:	3600 psi
Plant:	Plant 1	Strength:	3000 (psi)
On-Site Admixtures:	None		

Field Measurements			
Weather:	Over Cast/ Drizzling	Slump (in):	4-3/4
Air Temperature (F):	65	Concrete Temp (F):	73
		Plastic Unit Weight:	
		Air Content:	
		Load Volume:	9.00 (yd³)

Standard Cure		Field Cure	
Initial Cure Method:	Plastic Cover/Lid/Blanket		
Final Cure Method:	Water Storage Tank		


Lab Test Results

Testing Lab: B2Z Mission Lab, 900 S. Stewart Rd., Suite 2, Mission, TX, 78572

Specimen Number	Test Age Days	Test Date	Field / Lab Cure Days	Average Cylinder Diameter (in)	Cylinder Area (in²)	Max Load (lbs)	Strength (psi)	Fracture Type	Break Remark	Capping Method
2-1	7	12/13/24	1 / 6	4.00	12.57	44,899	3,570	2	R3	1
2-2	7	12/13/24	1 / 6	4.00	12.57	46,099	3,670	2	R3	1
2-3	28	01/03/25	1 / 27	4.00	12.57	63,033	5,020	3	R6	1
2-4	28	01/03/25	1 / 27	4.00	12.57	67,285	5,350	3	R6	1
2-5	56	01/31/25	1 / 55							

Test Age Average Strengths (psi): 7 Day - 3620, 28 Day - 5180

Capping Methods	
R3: The 7 day test results meets or exceeds the 28 day specified strength. R6: The 28 day test results meets or exceeds the 56 day specified strength. Tested By: Jaykob Quintanilla (1,2,3,4) Checked In : 12/07/2024 (1,2,3,4,5)	1: Neoprene Pad



Respectfully Submitted by B2Z Engineering

Jorge Solis
Jorge Solis, Laboratory Manager