



P.O. Box 2724  
 McAllen, Tx. 78502  
 (956) 585-3773

## Invoice

Date	Invoice #
7/11/2025	30093

Please send remittance with copy of invoice to:

Attn: Mrs. Aisha Gonzalez  
 P.O. Box 2724  
 McAllen, Tx. 78502

**Bill To:**

Hidalgo County Precinct #3  
 724 Breyfogle Rd.  
 Mission, TX 78574

**Project Info:**


El Paraiso Project (C-22-0213-09-06)  
 WA#2 - El Paraiso Health Clinic  
 PO# 872577  
 B2Z JOB #: 3101B

**Billing Period** June 2025

Description	Contract	Previous Applications	Current Completed	Total Completed	% Complete
Construction Material Testing Services (CMT)	\$ 47,615.80	\$ 45,235.01	\$ 2,380.79	\$ 47,615.80	100.0%
<b>Total For This Billing Period</b>					<b>\$2,380.79</b>

**Work Authorization ~ Summary**

WA No.	WA Amount	Previously Inv.	Percent Complete	Remaining Balance
2	\$47,615.80	\$45,235.01	100%	\$0.00



Aisha Gonzalez - President

El Paraiso Clinic | ARPA-21-340-019  
 P.O. # 872577  
 Acct. # 5-1290-441-12-115-215-6-452

Approved  
 Gilbert Gallegos, AIA  
 07/16/2025

**Mission Office**

900 S Stewart Rd, Ste. 2  
Mission, TX 78572  
Phone: 956-585-3773

**Client:**

Hidalgo County  
100 North Closser  
Edinburg, TX 78539

**Project:**

3101B  
El Paraiso- Health Clinic "A"  
1901 N. Los Ebanos Rd.  
Alton, TX 78573

**Sample Details**

Set #:	10	Technician:	Jorge Solis	Batched:	09:15 CDT
Specimen Size:	4 x 8 Cast Cylinder	Cast By:	Jorge Solis	Sampled:	10:25 CDT
Specimens In Set:	5	Date Cast:	10/12/24	Cast:	10:30 CDT
Truck / Ticket #:	10075203 / 48620989	Sampled From:	Chute	Truck Empty:	10:24 CDT
Contractor:	N.M Construction	Placement Method:	Pump	Placement Time:	69 (min)

**Location**

Placement Location:	Footing
Location Details:	N.W Entrance
Sample Location / Notes:	Perimeter Footing

**Batch Log**

Supplier:	Cemex	Mix Design:	4000 1" F 3-5"	Strength:	3000 (psi)
Plant:	4207-A Edinburg				
On-Site Admixtures:	None				

**Specifications**

**Field Measurements**

Weather:	Sunny	Slump (in):	6	Plastic Unit Weight:	
Air Temperature (F):	82	Concrete Temp (F):	87	Air Content:	
				Load Volume:	9.00 (yd <sup>3</sup> )

**Standard Cure**

Min / Max Temp (F):	82/94
Initial Cure Method:	Plastic Cover/Lid/Blanket
Final Cure Method:	Water Storage Tank

**Field Cure**

**Lab Test Results**


Testing Lab: B2Z Mission Lab, 900 S. Stewart Rd., Suite 2, Mission, TX, 78572

Specimen Number	Test Age Days	Test Date	Field / Lab Cure Days	Average Cylinder Diameter (in)	Cylinder Area (in <sup>2</sup> )	Max Load (lbs)	Strength (psi)	Fracture Type	Break Remark	Capping Method
10-1	7	10/19/24	2 / 5	4.00	12.57	37,272	2,970	2	F3	1
10-2	7	10/19/24	2 / 5	4.00	12.57	37,466	2,980	2	F3	1
10-3	28	11/09/24	2 / 26	4.00	12.57	51,884	4,130	2	R6	1
10-4	28	11/09/24	2 / 26	4.00	12.57	53,650	4,270	3	R6	1
10-5	56	12/07/24	2 / 54							

Test Age Average Strengths (psi): 7 Day - 2970, 28 Day - 4200

**Capping Methods**

F3: The 7 day test results did not meet the specifications. R6: The 28 day test results meets or exceeds the 56 day specified strength. Tested By: Jaykob Quintanilla (1,2,3,4) Checked In : 10/14/2024 (1,2,3,4,5)	1: Neoprene Pad
--	-----------------



Respectfully Submitted by B2Z Engineering

*Jorge Solis*  
Jorge Solis, Laboratory Manager

**Mission Office**

900 S Stewart Rd, Ste. 2  
Mission, TX 78572  
Phone: 956-585-3773

**Client:**

Hidalgo County  
100 North Closer  
Edinburg, TX 78539

**Project:**

3101B  
El Paraiso- Health Clinic "A"  
1901 N. Los Ebanos Rd.  
Alton, TX 78573

Sample Details					
Set #:	11	Technician:	Jorge Solis	Batched:	11:03 CDT
Specimen Size:	4 x 8 Cast Cylinder	Cast By:	Jorge Solis	Sampled:	12:00 CDT
Specimens In Set:	5	Date Cast:	10/12/24	Cast:	12:05 CDT
Truck / Ticket #:	10068763 / 486221018	Sampled From:	Chute	Truck Empty:	12:21 CDT
Contractor:	NM Construction	Placement Method:	Pump	Placement Time:	78 (min)

Location	
Placement Location:	Footing
Location Details:	South Side
Sample Location / Notes:	Perimeter Footing

Batch Log		Specifications	
Supplier:	Cemex	Mix Design:	4000 1" F 3-5"
Plant:	4207-A Edinburg	Strength:	3000 (psi)
On-Site Admixtures: None			

Field Measurements			
Weather:	Sunny	Slump (in):	5
Air Temperature (F):	87	Concrete Temp (F):	88
		Plastic Unit Weight:	
		Air Content:	
		Load Volume:	54.00 (yd <sup>3</sup> )

Standard Cure		Field Cure	
Min / Max Temp (F):	82/94		
Initial Cure Method:	Plastic Cover/Lid/Blanket		
Final Cure Method:	Water Storage Tank		


**Lab Test Results**

Testing Lab: B2Z Mission Lab, 900 S. Stewart Rd., Suite 2, Mission, TX, 78572

Specimen Number	Test Age Days	Test Date	Field / Lab Cure Days	Average Cylinder Diameter (in)	Cylinder Area (in <sup>2</sup> )	Max Load (lbs)	Strength (psi)	Fracture Type	Break Remark	Capping Method
11-1	7	10/19/24	2 / 5	4.00	12.57	39,228	3,120	3	R3	1
11-2	7	10/19/24	2 / 5	4.00	12.57	39,338	3,130	3	R3	1
11-3	28	11/09/24	2 / 26	4.00	12.57	47,367	3,770	2	R6	1
11-4	28	11/09/24	2 / 26	4.00	12.57	50,212	4,000	3	R6	1
11-5	56	12/07/24	2 / 54							

Test Age Average Strengths (psi): 7 Day - 3130, 28 Day - 3880

Capping Methods	
R3: The 7 day test results meets or exceeds the 28 day specified strength. R6: The 28 day test results meets or exceeds the 56 day specified strength. Tested By: Jaykob Quintanilla (1,2,3,4) Checked In : 10/14/2024 (1,2,3,4,5)	1: Neoprene Pad



Respectfully Submitted by B2Z Engineering

*Jorge Solis*  
Jorge Solis, Laboratory Manager

**Client:**Hidalgo County  
100 North Closner  
Edinburg, TX 78539**Project:**3101B  
El Paraiso- Health Clinic "A"  
1901 N. Los Ebanos Rd.  
Alton, TX 78573**Project Contractor:** NM Contracting

On 11/21/2024, a representative of B2Z Engineering was dispatched to the subject project to perform a rebar inspection. Please see attached report.

<b>Contractor/Inspector Present:</b>	NM Contracting
<b>Inspector/Technician Time:</b>	2.0
<b>Trip Charge:</b>	
<b>Inspector/Technician:</b>	Other Manuel Ornelas

Respectfully Submitted by B2Z Engineering

  
\_\_\_\_\_  
Jorge Solis, Laboratory Manager